

12	T800	M21	[90/90/0/0/45/45/-45/-45/ 90/0/45/-45]s	OHT_D7	RTD	475
----	------	-----	--	--------	-----	-----

번호	Lami	Resin	Layup	Test	Conditions	Simulation [MPa]
13	G40-800	Epoxy	[45/90/-45/90/0/90/45] S	UNT	RTD	454.4
14	G40-800	Epoxy	[45/90/-45/90/45/0/-45 /90/45]S	UNT	RTD	531.0
15	G40-800	Epoxy	[45/90/-45/0/-45/45/90 /45/-45]S	UNT	RTD	565.5
16	G40-800	Epoxy	[45/90/-45/0/-45/45/-4 5/45/-45/0]S	UNT	RTD	463.4
17	G40-800	Epoxy	[45/90/-45/0/-45/45/90 /0/45/-45]S	UNT	RTD	881.9
18	G40-800	Epoxy	[45/90/-45/0/-45/45/0/ 45/-45/0]S	UNT	RTD	960.0
19	G40-800	Epoxy	[45/90/-45/0/90/0/45/0 /45/-45]S	UNT	RTD	974.5
20	G40-800	Epoxy	[45/90/-45/0/90/0/-45/ 45]S	UNT	RTD	1061.7
21	G40-800	Epoxy	[45/90/-45/0/-45/90/0/ 45/-45/0]S	UNT	RTD	984.7
22	G40-800	Epoxy	[45/90/-45/0/-45/45/0/ 45/-45/0]S	UNT	RTD	1206.8
23	G40-800	Epoxy	[45/90/-45/0/90/0/90/0 /90/0]S	UNT	RTD	1310.4
24	G40-800	Epoxy	[45/90/-45/0/45/0/-45/ 0/45]S	UNT	RTD	1645.1
25	G40-800	Epoxy	[45/90/0/-45/0/90/0]S	UNT	RTD	1850.2
26	G40-800	Epoxy	[45/90/0/-45/0/45/0]S	UNT	RTD	1924.8

번호	Lami	Resin	Layup	Test	Conditions	Simulation [MPa]
27	G40-800	Epoxy	[45/90/-45/90/0/90/45]S	OHT	RTD	240.4
28	G40-800	Epoxy	[45/90/-45/90/45/0/-45/90/45]S	OHT	RTD	355.0
29	G40-800	Epoxy	[45/90/-45/0/-45/45/90/45/-45]S	OHT	RTD	426.9
30	G40-800	Epoxy	[45/90/-45/0/-45/45/-45/45/-45/0]S	OHT	RTD	359.7
31	G40-800	Epoxy	[45/90/-45/0/-45/45/90/0/45/-45]S	OHT	RTD	499.3
32	G40-800	Epoxy	[45/90/-45/0/-45/45/0/45/-45/0]S	OHT	RTD	449.2
33	G40-800	Epoxy	[45/90/-45/0/90/0/45/0/45/-45]S	OHT	RTD	523.4
34	G40-800	Epoxy	[45/90/-45/0/90/0/-45/45]S	OHT	RTD	539.7
35	G40-800	Epoxy	[45/90/-45/0/-45/90/0/45/-45/0]S	OHT	RTD	565.7
36	G40-800	Epoxy	[45/90/-45/0/-45/45/0/45/-45/0]S	OHT	RTD	558.2
37	G40-800	Epoxy	[45/90/-45/0/90/0/90/0/90/0]S	OHT	RTD	639.6
38	G40-800	Epoxy	[45/90/-45/0/45/0/-45/0/45]S	OHT	RTD	738.4
39	G40-800	Epoxy	[45/90/0/-45/0/90/0]S	OHT	RTD	768.3
40	G40-800	Epoxy	[45/90/0/-45/0/45/0]S	OHT	RTD	816.7